



RadanTahrir Co.  
Radan Carbonless Papers  
www.radantahrir.com

## Technical Specifications

Property	Standard	Units	CB		CFB		CF	
			Value	Tolerance	Value	Tolerance	Value	Tolerance
Substance	ISO 536 : 1995	g/m <sup>2</sup>	52	±4%	53	±4%	52	±4%
Whiteness	ISO 11475 : 2004	CIE	136	±6	105	±6	99	±6
Relative Humidity	TAPPI T502 om-89	%	43	±5	43	±5	43	±5
Curling	TAPPI T427 um-85	Mm	-2.0	(4.0) - 0.0	-2.0	(4.0) - 0.0	-2.0	(4.0) - 0.0
Thickness	ISO 534 : 2005	µm	77	±4	68	±4	66	G≤90 = ±4 G≥130 = ±4

CB: Coated Back Carbonless paper  
CFB: Coated Front and Back Carbonless paper  
CF: Coated Back Carbonless paper

Values are subject to change without notice.  
Last update 2010/11



ISO 9001-2000